

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 March 2002 (07.03.2002)

PCT

(10) International Publication Number
WO 02/18533 A1

- (51) International Patent Classification⁷: **C11D 17/04**
- (21) International Application Number: **PCT/GB01/03936**
- (22) International Filing Date:
3 September 2001 (03.09.2001)
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:
0021585.5 1 September 2000 (01.09.2000) **GB**
0109584.3 19 April 2001 (19.04.2001) **GB**
- (71) Applicant (*for all designated States except US*):
RECKITT BENCKISER (UK) LIMITED [GB/GB];
103-105 Bath Road, Slough, Berkshire SL1 3UH (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **MCKECHNIE, Malcolm, Tom** [GB/GB]; Spring Rise, 12A North Road, Lund, Driffield, East Yorkshire YO25 9TF (GB). **MUIR, Neil** [GB/GB]; 12 Fairfield View, Welton, East Yorkshire HU15 1PZ (GB). **COKE, Mark** [GB/GB]; 18 Todds Close, Swanland, East Yorkshire HU14 3NT (GB).
- (74) Agents: **BROWN, Andrew, Stephen** et al.; Reckitt Benckiser plc, Group Patents Dept., Dansom Lane, Hull HU8 7DS (GB).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— *with international search report*
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: **CLEANING METHOD**

(57) Abstract: A cleaning method employs a textile article immersed in or retaining water. The textile article has calcium-binding moieties to soften the wash water and improve cleaning.

BEST AVAILABLE COPY

WO 02/18533 A1

CLEANING METHOD

This invention relates to a method of cleaning using water, in which the water is softened and/or in which the
5 deposition of hard water scale is diminished. The invention relates in particular to such a method carried out in a domestic environment.

It is well known that certain metal compounds, notably
10 calcium compounds, when present in water, have a significant effect on the properties of the water. "Hard" water containing a significant loading of soluble calcium and magnesium compounds forms a scum with soap or
15 detergent and may require a large amount of soap or detergent in order to form a lather. Scale deposits can readily form from such water, for example on heating or pH change or evaporation. These can be encrustations, or watermarks left on evaporation of water droplets from, especially, a shiny surface.

20

There have been many proposals for removal of metal ions from aqueous solutions. In the industrial context proposals have included filter beds and polymeric filters for capturing heavy metal ions from an aqueous solution
25 flowing within a passageway. Examples are given in EP 992238A and GB 20869564A. In the domestic context chelating compositions can be added to an aqueous washing solution and these can capture metal ions, such as calcium ions. Examples of chelating compositions are given in EP-
30 A-892040. However in a multi-step washing process, such as that carried out by a clothes washing machine, it can be a problem that the chelating agent is discharged, with the water, at an intermediate stage of the process.

CONFIRMATION COPY

There is a need for a technology which can bind metal ions, at least calcium ions and preferably other metal ions in addition, in a convenient manner, through the
5 entire course of a cleaning procedure.

In accordance with a first aspect of the present invention there is provided a cleaning method which employs a textile article immersed in or retaining water,
10 the textile article having calcium-binding moieties. Suitably the textile article and/or the water contains a cleaning agent, for example a surfactant.

Preferably the cleaning method is for cleaning
15 household articles.

The method of cleaning may be a method of ware washing using a machine, for example a clothes' washing machine or a dishwashing machine.

20

In such methods the cleaning water is suitably produced by dissolution of a liquid or solid cleaning concentrate in the machine, at or immediately after the start of the washing operation. Such concentrates suitably
25 include one or more of an anionic surfactant, a non-ionic surfactant, an amphoteric surfactant or a cationic surfactant. For machine washing anionic and non-ionic surfactants are preferred.

30 A suitable anionic surfactant is an anionic organic surfactant, which is usually employed in a soluble salt form, preferably as an alkali metal salt, especially as a sodium salt. Although other types of anionic detergents

may be utilized, such as higher fatty acyl sarcosides, alkyl sulphosuccinates, alkyl ether sulphosuccinates, alkylamide sulphosuccinates, alkyl sulphosuccinates, alkyl sulphoacetates, alkyl phosphates, alkyl ether phosphates, acyl isothionates, N-acyl taurates and acyl lactylates, or conventional "soaps" of fatty acids, the preferred anionic surfactants employed are those which are described as being of a sulphonate or sulphate type. These include linear higher alkylaryl sulphonates (for example alkylbenzene sulphonates), alkyl sulphates, alkyl ether sulphates, alkylamidoether sulphates, alkylarylpolyether sulphates, monoglyceride sulphates, alkyl sulphonates, alkylamido sulphonates, higher fatty alcohol sulphates, higher fatty alcohol polyalkoxylate sulphates, olefin sulphonates, α -methyl ester sulphonates and paraffin sulphonates. An extensive listing of anionic detergents, including such sulph(on)ate surfactants, is given at pages 25 to 138 of the text Surface Active Agents and Detergents, Vol. II, by Schwartz, Perry and Berch, published in 1958 by Interscience Publishers, Inc., and is incorporated herein by reference. Usually the higher alkyl group of such anionic surfactants is of 8 to 24, especially 10 to 20 carbon atoms, preferably 12 to 18 carbon atoms, and the alkoxyate content of such anionic surfactants that are alkoxyated (preferably ethoxyated or ethoxyated/propoxyated) is in the range of 1 to 4 alkoxy groups per mole.

One preferred class of anionic surfactants comprise the alkali metal (preferably sodium) alkyl sulphates, preferably having linear C₁₂₋₁₈ alkyl groups.


Another preferred class of anionic surfactants comprise alkali metal (preferably sodium) alkylaryl sulphonates (especially alkylbenzene sulphonates), preferably having linear C₁₀₋₁₃ alkyl groups.

5

A preferred non-ionic surfactant is a condensation product of a higher fatty alcohol or alkyl phenol with a lower alkylene oxide, such as ethylene oxide or a mixture of ethylene oxide and propylene oxide. In such non-ionic
10 surfactants the higher fatty moiety will normally be of 7 to 16 carbon atoms and there will usually be present from 3 to 20, preferably 4 to 15 moles of alkylene oxide per mole of higher fatty alcohol.

15 Another class of non-ionic surfactants that could be used are sorbitan esters of fatty acids having from 10 to 24 carbon atoms, for example sorbitan mono-oleate.


Amphoteric surfactants which may be used include
20 amphoteric betaine surfactant compounds having the following general formula:



25 wherein R is a hydrophobic group which is an alkyl group containing from 10 to 22 carbon atoms, preferably from 12 to 18 carbon atoms, an alkylaryl or arylalkyl group containing a similar number of carbon atoms with a benzene ring being treated as equivalent to about 2 carbon atoms,
30 and similar structures interrupted by amido or ether linkages; each R₁ is an alkyl group containing from 1 to 3 carbon atoms; and R₂ is an alkylene group containing from

1 to 6 carbon atoms.

Examples of cationic surfactants which may be used include quaternary ammonium compounds and salts thereof, including quaternary ammonium compounds which also have germicidal activity and which may be characterized by the general structural formula:




when at least one of R_1 , R_2 , R_3 and R_4 is a hydrophobic, aliphatic, aryl aliphatic or aliphatic aryl group containing from 6 to 26 carbon atoms, and the entire cationic portion of the molecule has a molecular weight of at least 165. The hydrophobic groups may be long-chain alkyl, long-chain alkoxy aryl, long-chain alkyl aryl, halogen-substituted long-chain alkyl aryl, long-chain alkyl phenoxy alkyl or aryl alkyl. The remaining groups on the nitrogen atoms, other than the hydrophobic radicals, are generally hydrocarbon groups usually containing a total of no more than 12 carbon atoms. The radicals R_1 , R_2 , R_3 and R_4 may be straight chain or may be branched, but are preferably straight chain, and may include one or more amide or ester linkages. The radical X may be any salt-forming anionic radical.

30

Examples of quaternary ammonium salts within the above description include the alkyl ammonium halides such

as cetyl trimethyl ammonium bromide, alkyl aryl ammonium halides such as octadecyl dimethyl benzyl ammonium bromide, and N-alkyl pyridinium halides such as N-cetyl pyridinium bromide. Other suitable types of quaternary ammonium salts include those in which the molecule contains either amide or ester linkages, such as octyl phenoxy ethoxy ethyl dimethyl benzyl ammonium chloride and N-laurylcocoaminoformylmethyl)-pyridinium chloride. Other effective types of quaternary ammonium compounds which are useful as germicides includes those in which the hydrophobic radical is characterized by a substituted aromatic nucleus as in the case of lauryloxyphenyltrimethyl ammonium chloride, cetylaminophenyltrimethyl ammonium methosulphate, dodecylphenyltrimethyl ammonium methosulphate, dodecylphenyltrimethyl ammonium chloride and chlorinated dodecylphenyltrimethyl ammonium chloride.

Preferred quaternary ammonium compounds which act as germicides and which are useful in the present invention include those which have the structural formula:



wherein R₂ and R₃ are the same or different C₈-C₁₂alkyl, or R₂ is C₁₂-C₁₆alkyl, C₈-C₁₈alkylethoxy, C₈-C₁₈alkyl-phenolethoxy and R₃ is benzyl, and X is a halide, for example chloride, bromide or iodide, or methosulphate. The alkyl groups R₂ and R₃ may be straight chain or branched, but are preferably substantially linear.

In any method of the invention, a mixture of two or more surfactants may be used. Other known surfactants not particularly described above may also be used. Such
5 surfactants are described in McCutcheon's Detergents and Emulsifiers, North American Edition, 1982; Kirk-Othmer, Encyclopaedia of Chemical Technology, 3rd Ed., Vol. 22, pp 346-387.

10 It is preferred that the cleaning agent used in a machine washing method contains a builder. Suitable builders include water-soluble inorganic salt builders, preferably sodium salts, such as sodium polyphosphates, e.g. sodium tripolyphosphate and sodium pyrophosphate,
15 sodium carbonate, sodium bicarbonate, sodium sesquicarbonate, sodium silicate, sodium disilicate, sodium metasilicate and sodium borate. In addition to the water-soluble inorganic salts, water-insoluble builders may also be useful, including the ion exchanging zeolites, such as
20 Zeolite 4A. Organic builders may also be employed. Among suitable organic builders are polyacetal carboxylates, as described in US-B-4725455, and water-soluble salts of lower hydroxycarboxylic acids, such as sodium citrate and sodium gluconate.

25 The cleaning method may be a manual method, for example using a hand-cloth or mop, and an open vessel, for example a bucket or bowl. Thus, the cleaning method could be a method of cleaning a hard surface, for example a
30 window, tiled surface, shower screen, tableware and kitchenware, a sanitaryware article, for example a shower screen, lavatory, wash basin or sink, a car (defined herein as a "household article") or a kitchen worktop.

In such methods the cleaning agent is dissolved in water prior to the start of cleaning. The cleaning agent may comprise an anionic surfactant and/or a non-ionic
5 surfactant, as described above. Additionally or alternatively, the cleaning agent may include one or more of an amphoteric surfactant and a cationic surfactant, as described above.

10 A composition used in the invention may optionally include one or more conventional additives known to be useful in cleaning compositions including bleaching agents, viscosity modification agents, fragrances (natural or synthetically produced), foaming or foam-control
15 agents, solvents, fillers, colouring agents, and in the case of compositions for fabric washing, fabric conditioning agents, enzymes, hydrotropes and dye anti-redeposition agents. If the composition does not contain a cationic surfactant having germicidal properties as
20 detailed above, a germicidal agent may be incorporated as an optional ingredient into the cleaning agents used in the invention. Examples are phenolic group containing compounds such as o-phenyl-phenol, o-benzyl[p-chlorophenol] and 4-tert-amylphenol.

25

The textile article acts as a water softener within a vessel containing water, for example a bucket, sink or ware-washing machine. By capturing metal ions, notably calcium ions, the cleaning agent(s) present in the water
30 can work more effectively, and/or the vessel is soiled or scaled less, whether by soap scum or by encrustations or by watermarks left when droplets on a surface evaporate.

Preferably the textile article is such that calcium ions are captured throughout the method of cleaning.

Preferably the textile article is able to move freely
5 within the water used in the cleaning method. Thus, it is preferably not in the form of a filter or like body, retained in a fixed orientation, or mounted on a frame.

In the cleaning method the textile article is
10 preferably a sheet, for example a woven, knitted or non-woven sheet. The sheet may if wished be secured to one or more further sheets, which may be of the same or different material, forming a ply. Alternatively the textile article may be in the form of a thick yarn, or braid.
15 Alternatively it may be in the form of fibres or filaments, which may, for example, be tied together in a bundle, for example in a tassel or pom-pom, or retained in a water-permeable bag. Most preferably the textile article is a fabric sheet of relatively open form, for
20 example a non-woven fabric or a woven fabric of scrim form.

The textile article may if wished be contained within a rigid or flexible structure in which liquid inlet and
25 liquid outlets are provided to allow ingress and egress of water. Such a container may be for instance a cloth bag or a plastic cage.

It will be appreciated that the textile article can
30 improve cleaning by acting as a water softener, by facilitating capture of metal ions, notably calcium ions, from the water.

Preferably the textile article is also able to bind magnesium ions. Most preferably it is able to bind further ions, for example copper and iron ions. Preferably the moieties which are able to bind calcium
5 ions are also able to bind such further ions, notably magnesium ions.

The textile article could be discarded after use, or it could be regenerated, for example using sodium chloride
10 to effect cation exchange. A dye could be employed to give a colour change, on exhaustion of the available calcium-binding moieties on the textile article.

Most preferred is a method which employs a textile
15 article having polymeric fibres with calcium-binding side chains.

Such polymeric fibres may have one type of side chain or two, or more, types of side chain, able to bind
20 different metal ions.

The polymeric fibres may be prepared in any of a number of ways. The side chains may be grafted onto the fibres, for example using the well-known techniques of
25 radiation (or ionisation) grafting or chemical grafting. Radiation grafting is described in WO 94/12545. Chemical grafting is described in GB 2086954A. Alternatively, for certain side-chains the polymeric fibres may be fabricated (for example melt spun) already bearing the side-chains,
30 as described in EP 486934A. In yet other embodiments the polymeric fibres not bearing the side-chains may be coated with material which has the side-chains. The polymeric fibres may, in effect, be regarded as carrying the side-


chains by mechanical adhesion. Alternatively they may be attached by cross-linking, as described in EP 992283A.

Preferably the calcium-binding side-chains are any
5 side-chains which can be carried by polymeric fibres of textile character, and which are able to bind calcium (and preferably other) ions, and whose effectiveness in doing that is not substantially diminished by a cleaning agent. Suitable calcium-binding side-chains include residues of
10 acids, for example of acrylic or methacrylic acid, or carboxylic acids, or of sulphonic acids, or of phosphonic acids. Residues of organic acids are preferred. Particularly preferred are residues of methacrylic or, especially, acrylic acid.

15

Alternative calcium-binding side chains may include amino groups, quaternary ammonium salt groups and iminodicarboxyl groups $-N\{(CH_2)_nCOOH\}_2$, where n is 1 or 2. Further suitable calcium-binding side chains may include
20 residues of alginic compounds, for example of alginic acid and of alginates.


Further suitable calcium-binding side chains may include acyl groups as described in EP 984095A. These
25 have the formula



where X represents a residue in which one carboxyl group
30 is eliminated from a monocarboxylic acid or dicarboxylic acid;

V represents hydrogen or a carboxyl group;

M represents hydrogen; or



wherein R^1 represents a residue in which one hydrogen is eliminated from a carbon chain in an alkylene group, R^2 represents a direct bond or an alkylene group, Y^1 and Y^2 are the same or different and each represents hydrogen, a carboxyl group, an amino group, a hydroxy group or a thiol group, n is an integer of 1 to 4, M' represents hydrogen or



wherein R^3 represents a residue in which one hydrogen is eliminated from a carbon chain in an alkylene group; R^4 represents a direct bond or an alkylene group, Y^3 and Y^4 are the same or different and each represents hydrogen, a carboxyl group, an amino group, a hydroxy group or a thiol group; and Z represents hydrogen or has the same meaning as that of M .

Such side-chains are preferably carried by polymeric fibres selected from polyolefins, poly(haloolefins), poly(vinylalcohol), polyesters, polyamides, polyacrylics, protein fibres and cellulosic fibres (for example cotton,

viscose and rayon), most preferably by polyolefins, polyaricylics and cellulosic fibres. Polyolefins are especially preferred, particularly polyethylene and polypropylene.

5

When side-chains are grafted onto the base polymeric fibres a preferred process is one in which the side-chains are grafted to the base polymeric fibre using irradiation, in an inert atmosphere, with immediate delivery to the irradiated fibres of acrylic acid. Preferably the radiation is electron beam or gamma radiation, to a total dose of 10-300 kGy, preferably 20-100 kGy. The acrylic acid is preferably of concentration 20-80 vol %, in water, and the temperature at which the acrylic acid is supplied to the irradiated textile article is preferably an elevated temperature, for example 30-80°C. Preferably the base polymeric fibres are polyethylene, polypropylene or cellulosic fibres. The reaction to introduce the side-chains may be carried out on the fibres as such or may suitably be carried out on an already-formed textile article, for example a braid or sheet.

Components other than such side-chains may be provided on the textile article in order to give, or improve, water softening, thereby assisting cleaning. Such components will provide three main types of method of action, described below.

1) Ion exchange agents - such agents include alkali metal (preferably sodium) aluminosilicates either crystalline, amorphous or a mixture of the two. Such aluminosilicates generally have a calcium ion exchange

capacity of at least 50 mg CaO per gram of aluminosilicate, comply with a general formula:



5


and incorporate some water. Preferred sodium aluminosilicates within the above formula contain 1.5-3.0 SiO₂ units. Both amorphous and crystalline aluminosilicates can be prepared by reaction between
10 sodium silicate and sodium aluminate, as amply described in the literature.

Suitable crystalline sodium aluminosilicate ion-exchange detergency builders are described, for example,
15 in GB 1429143 (Procter & Gamble). The preferred sodium aluminosilicates of this type are the well known commercially available zeolites A and X, and mixtures thereof. Also of interest is zeolite P described in EP 384070 (Unilever).

20

Another class of compounds are the layered sodium silicate builders, such as are disclosed in US-A-4464839 and US-A-4820439 and also referred to in EP-A-551375.

25 These materials are defined in US-A-4820439 as being crystalline layered, sodium silicate of the general formula



30

where

M denotes sodium or hydrogen,

x is from 1.9 to 4 and y is from 0 to 20.

Literature references describing the preparation of such materials include Glastechn. Ber. 37,194-200 (1964),
5 Zeitschrift für Kristallogr. 129, 396-404 (1969), Bull. Soc. Franc. Min. Crist., 95, 371-382 (1972) and Amer. Mineral, 62, 763-771 (1977). These materials also function to remove calcium and magnesium ions from water. Also covered are salts of zinc which have also been shown to be
10 effective water softening agents.

2) Ion capture agents - agents which prevent metal ions from forming insoluble salts or reacting with surfactants, such as polyphosphate, monomeric
15 polycarbonates, such as citric acid or salts thereof, EDTA, alginates, alginates.

3) Anti-nucleating agents - agents which prevent seed crystal growth, such as polycarbonate polymers, such as
20 polyacrylates, acrylic/maleic copolymers, and acrylic phosphonates.

In a preferred aspect such ingredient(s) may be impregnated into the textile fibre.

25

In a preferred aspect such ingredient(s) may be conveniently present on the textile article. Such ingredient(s) may be deposited on the textile article by dosing a solution to the textile article and evaporating
30 the solute. Spray drying techniques may be employed. Ionic charge may also be employed to reversibly bind anionic ionisable ingredients to the textile article.

The textile article can have bound to it such ingredients in the form of particles of a material, as described above, with those particles not being released from the textile article in use.

5

Alternatively the textile article could carry on it particles of a material, as described above, with those particles being washed from the textile article, and dissolved or dispersed in the wash water, in use.

10

Alternatively there can be a hybrid system in which some such particles remain on the textile article and some are washed off, during the method.

15

The washing off of particles of such materials may be rapid in water or may be slow/progressive. A slow-release system may be attractive in obtaining good activity, for example calcium binding, throughout a cleaning method.

20

A suitable method of applying the present invention involves the use of a textile article with calcium binding side chains, as defined above, and also carrying said further ingredient(s), preferably particles, as defined above.

25

Preferably the textile article is substantially without means to capture anionic species in the water.

In accordance with a second aspect of the invention there is provided a method of cleaning in a ware washing machine, the method including softening the water in the machine, using a textile article having calcium-binding moieties.

In the second aspect the textile article may be such that water is softened in the wash cycle. Preferably it is softened in the rinse cycle. Most preferably it is
5 softened both in the wash and in the rinse cycles.

The invention will now be described, by way of embodiment, with reference to the following examples.

10 **Example 1**

Grafting of acrylic acid onto polyethylene fibres.

Chopped polyethylene fibres of 20 mm length are placed in a plastic bag, purged with nitrogen and sealed. The
15 bag is irradiated with 10 MeV electrons from a linear accelerator. The total radiation dose is 30 kGy. The fibres are removed from the bag and immersed without delay in a nitrogen-purged aqueous solution containing 40 vol % acrylic acid for 45 minutes at 62°C. The grafted fibres
20 were extracted with water overnight.

Example 2

Use of the grafted fibres of Example 1

25 The fibres are placed in a small bag of non-woven polyethylene, which is heat sealed. The bag is placed in the drum of a washing machine, with the clothes, at the start of a washing cycle. It is removed, with the clothes, at the end of the cycle, having provided water
30 softening throughout the cycle, to assist the washing process.

Example 3

Grafting of acrylic acid onto non-woven viscose fleece

A non-woven viscose single layer fleece sheet is irradiated under a nitrogen atmosphere using an electron
5 beam accelerator operating at 175 kV, to a total dose of 300 kGy. The sheet is immediately immersed in a nitrogen-purged aqueous solution containing 60 vol % acrylic acid for 5 hours at 35°C. The grafted fabric is extracted overnight.

10

Example 4Use of the fabric of Example 3

The fabric of Example 3 is divided into sections of
15 size 15 cm x 15 cm.

One section is used in a clothes washing cycle in the manner described in Example 2 in order to give effective water softening, throughout the cycle.

20

Another section is used in a method of cleaning a car, as the final drying cloth, in order to achieve drying without leaving watermarks, ie the hard water residues of evaporated droplets.

25

Another section is used as a drying cloth in window cleaning. Drying is achieved without streaks or watermarks.

30

Another section is used in a method of removing light scale deposits from a shower enclosure. A small amount of shower cleaner is applied to the section, and the deposits are removed, using the fabric with a rubbing action.

Another section is used as a manual washing up cloth, to wash dirty kitchenware and tableware.

5 Example 5

Use of sandwiched radiation grafted cloth

A heat sealed laminate comprised a middle calcium sequestrant layer between two outer layers.

10

Composition of each outer layer:

20g/m² sheet weight, laid (non-woven) fibres, a blend of:

15 20% cellulose, 10 mm staple length

40% viscose, 10 mm staple length

20% polyester bicomponent, 6mm staple length

20% polyester bicomponent, 12mm staple length

20 Composition of middle layer:

75g/m² sheet weight, laid (non-woven) fibres, a blend of:

80% 10 mm staple length viscose fibres radiation grafted

25 with 7.5mM/g carboxylate functionality

10% polyester bicomponent, 6mm staple length

10% polyester bicomponent, 12mm staple length

30 A 4.5cm x 4.5cm piece of this cloth immersed for 30 minutes in 500ml hard water, at 60°C, reduced the calcium ion level from 170mg/l to 143mg/l (determined by EDTA titration).

Example 6Use of polyacrylate cloth

Polyacrylate fibres are made by copolymerising acrylic
5 acid, sodium acrylate, methacrylic acid and
hydroxypropylmethacrylic acid in an aqueous premix. `
Polymerisation is initiated by ammonium persulphate. The
resulting cross-linked polymer is extruded into a hot air
stream to form fibres. These fibres are then incorporated
10 with other fibres into a non-woven cloth. In this example
the cloth was of 145g/m² sheet weight, made up of:

50%wt polyacrylate fibre, described above

50%wt polyester bicomponent

15

A 4.5cm x 4.5cm piece of this cloth immersed for 30
minutes in 500ml hard water, at 60°C, reduced the calcium
ion level from 170mg/l to 138mg/l (determined by EDTA
titration).

20

Example 7Use of sandwiched polyacrylate cloth

This employed a fresh non-woven cloth as described in
25 Example 6, but also comprising a layer of 30g/m²
spunbonded polypropylene laminated onto both sides to give
a three layer structure.

A 4.5cm x 4.5cm piece of this cloth immersed for 30
30 minutes in 500ml hard water, at 60°C, reduced the calcium
level from 170mg/l to 148mg/l (determined by EDTA
titration).

Example 8Use of derivatised cellulose cloth

5 A cellulose based non-woven cloth is chemically derivatised to give polycarboxylate functionality. Thus, a chemically bonded cellulose non-woven sheet, 95g/m² weight, is derivatised with succinic anhydride to give 1.71mMol/g COOH.

10

A 4.5cm x 4.5cm piece of this cloth immersed for 30 minutes in 500ml hard water, at 20°C, reduced the calcium level from 176mg/l to 154mg/l (determined by EDTA titration).

15

Example 9Machine wash tests

20 The cloths described in Examples 5, 6 and 7 were used in washing machine testing in order to assess calcium carbonate encrustation on the heating element. The washing machine employed was a CANDY 80 PLUS. Each washing load was 3.5 kg. A 60°C programme was selected. The water hardness was 172 mg/l Ca²⁺. The detergent
25 employed was 168g DASH ESSENTIAL, a commercial washing powder available in supermarkets in Italy, having the following composition (by weight):

30 anionic surfactant	11.7%
zeolite	18.9%
sodium silicate	2.7%
sodium citrate	3.5%

	sodium carbonate	25.9%
	sodium percarbonate	11.5%
	TAED	1.4%
	Protease	0.2%
5	Amylase	0.8%
	Phosphonate	0.3%
	Polymer	1.6%

Prior to the experiments the washing machine element
10 was weighed. It was re-weighed after 15 washes. The
results were as follows:

	Detergent alone	660mg HEE
	Detergent + Ex.5 cloth but mono-ply	540mg HEE
15	Detergent + Ex.5 tri-ply cloth	560mg HEE
	Detergent + Ex.6 mono-ply cloth	430mg HEE
	Detergent + Ex.7 tri-ply cloth	450mg HEE

HEE = Heating Element Encrustation

20

All cloths were approximately 625cm² in area and a
fresh cloth was used for each wash cycle.

Example 10

25 Use of derivatised viscose fibres in a bag

In further experiments JR Crompton's SUPERSEAL (trade
mark) three-ply tea bag paper, Ref. No. 478404, grammage
26.0 gsm was used to retain radiation grafted viscose
30 fibres. The chopped viscose fibres had been irradiated
using the method described for Example 1, under a nitrogen
atmosphere using an electron-beam accelerator. Once the
dosage had reached a specified value in kGy the fibres had

been immersed immediately in a nitrogen-purged aqueous solution of acrylic acid, at a moderately elevated temperature.

- 5 A first bag, 7cm x 7cm, contained 0.884g of functionalised fibres (19% dry weight) between the two paper sheets, and reduced the calcium ion concentration of a hard water from 174.3 ppm to 132.3 ppm (determined by EDTA titration).

10

 A second bag, 7cm x 7cm, contained 1.768g of functionalised fibres between the two paper sheets and reduced the calcium ion concentration of a hard water from 168.3 ppm to 92.3 ppm (determined by EDTA titration).

CLAIMS

1. A cleaning method which employs a textile article
immersed in or retaining water, the textile article having
5 calcium-binding moieties.

2. A method as claimed in claim 1, wherein the textile
article has polymeric fibres with calcium-binding side
chains.

10

3. A method as claimed in claim 2, wherein the side
chains are attached to the polymeric fibre by radiation
grafting.

15 4. A method as claimed in claim 2, wherein the side
chains are attached to the polymeric fibres by chemical
grafting; or by coating base fibres with a composition
carrying the side chains, and cross-linking the side
chains to the base fibres and/or relying on adhesion to
20 retain them; or wherein they are present already in the
as-formed fibres.

5. A method as claimed in claim 2, 3 or 4, wherein the
side chains are residues of organic acids.

25

6. A method as claimed in claim 5, wherein the side
chains are residues of acrylic or methacrylic acid, or of
sulphonic acids, or of phosphonic acids.

30 7. A method as claimed in any preceding claim, wherein
the polymeric fibres to which the side chains are attached
are selected from polyolefins, poly(haloolefins),

poly(vinylalcohols), polyesters, polyamides, polyacrylics, protein fibres and cellulosic fibres.

8. A method as claimed in claims 2 to 7, wherein the
5 textile article changes colour on exhaustion of the available calcium-binding side chains.

9. A method as claimed in any preceding claim, wherein the textile article has bound to it calcium-binding
10 particles.

10. A method as claimed in any preceding claim, wherein the textile article is a carrier for calcium-binding particles which dissolve or disperse in water with which
15 the textile article is in contact.

11. A method as claimed as preceding claim, which is a ware washing method using a ware washing machine.

20 12. A method as claimed in any preceding claim, in which the method comprises removing scale or diminishing its deposition.

13. A method as claimed in any preceding claim, wherein
25 the textile article is a cloth.

14. A method as claimed in claim 13, wherein the textile article is a non-woven sheet.

30 15. A method as claimed in any preceding claim, wherein the calcium-binding moieties are also able to bind magnesium ions.

16. A method as claimed in any preceding claim, wherein the textile article contains water softening agents selected from

- 5 1) an ion exchange agent,
 2) an ion capture agent, and
 3) an anti-nucleating agent.

17. A method of improving the operation of a ware washing
10 machine, by softening the water therein, the method comprising using, in the machine, a textile article having calcium-binding moieties.

18. A method of cleaning substantially as hereinbefore
15 described with particular reference to the examples.

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C11D17/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C11D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 25 33 510 A (HOECHST AG) 10 February 1977 (1977-02-10) page 10, line 1 - line 30 page 4, line 4 - line 8 ---	1-7, 11-18
X	FR 2 192 208 A (HENKEL & CIE GMBH) 8 February 1974 (1974-02-08) page 2, line 6 - page 4, line 18 page 10, line 32 - line 34 ---	1-7, 11-18
X	DATABASE WPI Section Ch, Week 199423 Derwent Publications Ltd., London, GB; Class D15, AN 1994-188150 XP002182979 & JP 06 126278 A (TORAY IND INC), 10 May 1994 (1994-05-10) abstract --- -/--	1, 13-16, 18

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * & * document member of the same patent family

Date of the actual completion of the international search

16 November 2001

Date of mailing of the international search report

03/12/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Richards, M

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 255 148 A (REINWALD ELMAR ET AL) 10 March 1981 (1981-03-10) column 3, line 53 - line 54 column 6, line 40 - line 57 column 9, line 54 - line 57 -----	1,10-18
X	US 4 066 394 A (LEONARD RALPH SPENCER) 3 January 1978 (1978-01-03) column 1, line 65 -column 2, line 68 -----	1,9-18
A	US 4 128 399 A (LIOTTA LANCE A ET AL) 5 December 1978 (1978-12-05) column 4, line 40 - line 68 -----	1,8
A	US 3 434 864 A (HADEN WALTER L JR ET AL) 25 March 1969 (1969-03-25) claim 1 -----	8

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
DE 2533510	A	10-02-1977	DE 2533510 A1	10-02-1977
FR 2192208	A	08-02-1974	AT 323867 B	11-08-1975
			AU 5784673 A	09-01-1975
			BE 802009 A1	07-01-1974
			DE 2334162 A1	24-01-1974
			FR 2192208 A1	08-02-1974
			IT 990995 B	10-07-1975
			JP 49042977 A	23-04-1974
			NL 7309347 A	09-01-1974
			ZA 7304598 A	27-03-1974
JP 6126278	A	10-05-1994	NONE	
US 4255148	A	10-03-1981	AT 344122 B	10-07-1978
			AT 796974 A	15-11-1977
			BE 834116 A1	02-04-1976
			BR 7506415 A	10-08-1976
			CH 603877 A5	31-08-1978
			DE 2543946 A1	08-04-1976
			ES 441480 A1	01-04-1977
			FR 2286911 A1	30-04-1976
			GB 1521910 A	16-08-1978
			IT 1047272 B	10-09-1980
			JP 51091908 A	12-08-1976
			JP 59008320 B	23-02-1984
			NL 7511463 A	06-04-1976
			SE 429307 B	29-08-1983
			SE 7510898 A	05-04-1976
			ZA 7506264 A	29-09-1976
US 4066394	A	03-01-1978	CA 1064799 A1	23-10-1979
			DE 2556190 A1	01-07-1976
			FR 2296595 A1	30-07-1976
US 4128399	A	05-12-1978	NONE	
US 3434864	A	25-03-1969	NONE	

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.